



**TECHNICAL DATA SHEET**

<b>Order reference</b>	<b>RFODP100</b>
<b>Article number</b>	<b>813962</b>

<b>Date</b>	07/24/2009	<b>Replaces</b>	New	<b>No. Pages</b>	1
-------------	------------	-----------------	-----	------------------	---

**Product Description:**

<b>Style</b>	Oil Only Pads with Coverstock on both sides. Perforated on centerline for dividing in half for smaller applications.
<b>Item Size (each)</b>	38 cm x 48 cm
<b>Color</b>	Off-White
<b>Composition</b>	90% cellulose, 10% PP/PE spunbond coverstock (by weight). SB used to add strength and durability.
<b>Structure</b>	3 Ply - Nonwoven mat of randomly oriented cellulose fibers
<b>Absorbency</b>	<b>Hydrophobic + Oleophilic</b>
<b>Bonding</b>	Mechanical entanglement

<b>Intended Application</b>	Low lint Sorbent for Oil, or Solvent Base Liquids.
-----------------------------	--

<b>Absorbency Capacity</b>	148 l per case
----------------------------	----------------

**Packaging Description:**

Package configuration	1-case	Pkg. Weight	7.7 kg (6.7 kg)
Items per Package	100-Pads/Case	Pkg. Dimensions	50 cm x 40 cm x 62 cm H
Container type	Carton		

**Physical Properties:**

Parameter	SPC Test Method	Units	Nominal	(+/-)Tolerance
Basis Weight	SPCTM-002A	G/M2	235	23
Caliper	SPCTM-003A	mils	260	26
Absorbency** (med.visc.)	SPCTM-004B	gL/gS	30	3
Tensile Strength	SPCTM-007	kg	13.6	1.36
Color	Visual	-----	Off-White	per standard

**The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped. \*\* The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

<b>Attributes</b>	Product will be free of foreign material contamination, rips, holes, and tears.
<b>Labeling</b>	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
<b>Certification</b>	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.