



**TECHNICAL DATA SHEET**

<b>Order reference</b>	SA-AFA				
<b>Article number</b>	813830				
<b>Date</b>	4-11-11	<b>Replaces</b>	04-03-08	<b>No. Pages</b>	1

**Product Description:**

<b>Style</b>	Maintenance kit consisting of one (1) adsorbent roll (76 cm x 46 m, perforated every 76 cm) and one (1) anti-fatigue base mat (82 cm x 152 cm)
<b>Item Size (each)</b>	adsorbent roll (76 cm x 46 m, perforated every 76 cm), anti-fatigue base mat (82 cm x 152 cm)
<b>Color</b>	Adsorbent: grey/black; base mat: black
<b>Composition</b>	Adsorbent: 100% Polypropylene Base mat: 100% Nitrile rubber
<b>Structure</b>	Nonwoven mat of randomly oriented Micro-fibers [4-10 micron diameters]
<b>Absorbency</b>	Universal ( <b>Hydrophilic + Oleophilic</b> )

<b>Intended Application</b>	Low -Lint Chemical Resistant Sorbent for Water, Oil, or Solvent Base Liquids
-----------------------------	--

<b>Absorbency Capacity</b>	187 l per roll (saturated; medium viscosity)
----------------------------	--

**Packaging Description:**

<b>Package configuration</b>	2 Case	<b>Pkg. Weight</b>	10.8 kg (10.2 kg) + 14.5kg (14.3kg)
<b>Items per Package</b>	1 mat, 1 adsorbent roll	<b>Pkg. Dimensions</b>	20cm x 20cm x 95cm H + 49 cm x 49 cm x 105 cm H
<b>Container type</b>	Carton		

**Physical Properties:**

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
Basis Weight	SPCTM-002	G/M2	365	36
Caliper	SPCTM-020	mm	5.3	0.5
Absorbency** (med.visc.)	SPCTM-004B	gL/gS	12.5	2
Tensile Strength	SPCTM-007	daN	12.5	1.2
Color	Visual	-----	Grey/black	per standard

**The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.**

**\*\* The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

<b>Attributes</b>	Product will be free of foreign material contamination, rips, holes, and tears.
<b>Labeling</b>	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
<b>Certification</b>	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.

Brady Europe | Industriepark C3 Lindestraat 20 | B9240 Zele | Belgium |

Tel: +32 52.45.7811 | Fax: +32 52.45.7812

www.bradyeurope.com