

Product Information Sheet

B-424 Lab

Effective Date: 1/23/19

B-424 THERMAL TRANSFER PRINTABLE WHITE PAPER LABEL STOCK

This Product Information Sheet is focused on the suitability of B-424 for laboratory applications. For additional data regarding B-424 performance please refer to B-424 Technical Data Sheet.

Description: GENERAL

Print Technology: Thermal transfer

Material Type: Paper Finish: Matte white

Adhesive: Permanent latex

APPLICATIONS

Laboratory identification such as slides, bottles and general laboratory identification

REGULATORY APPROVALS

For information on the Weee-RoHS compliance status for a Brady Product go to one of the

following websites:

In Canada: www.bradycanada.ca/weee-rohs
In Europe: www.bradyeurope.com/rohs

In Japan: www.brady.co.jp/products/labelsuse/rohs
All other regions: www.bradyid.com/weee-rohs

RECOMMENDED RIBBONS

Brady Series R4300

Brady Series R4500 (colors - red, blue, green)

Brady Series R6100 (alternate)*

*B-424 can be printed with the Brady Series R6100 ribbon; please note that testing described in this product information sheet was performed on materials printed with the Brady Series R4300 ribbon.

Details:

Note: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D1000	
	-Total (excluding liner)	0.0889 mm (0.0035 inch)
Adhesion to:	ASTM D1000	
-Stainless Steel	20 minute dwell	Destroys upon removal from
-Polypropylene		all listed surfaces
-Glass		

PERFORMANCE PROPERTIES	LAB SIMULATED ENVIRONMENT

Performance properties tested on B-424 printed with the Brady Series R4300 ribbon. Printed samples were laminated to glass microscope slides, glass test tubes (1.1 cm outer diameter) and polypropylene centrifuge tubes (1.1 cm inner diameter, 1.5 ml capacity) and allowed to dwell 24 hours before exposure to the indicated environments.



ENVIRONMENT	TEST METHOD		TYPICAL RESULTS
High Service Temperature**	30 days at various temperatures		No visible effect at 50°C (122°F); at 60°C (140°F) label discolors slightly but still functional
Freezer	3 cycles of 16 hours at –70°C (–94°F)/ 8 hours at room temperature cycles	> > >	Glass test tube Polypropylene centrifuge tube Glass microscope slide
Pressure Cooker	3 cycles of 1 hour in 121°C (250°F) 15 psi pressure cooker/23 hour room temperature	* * *	Glass test tube Polypropylene centrifuge tube Glass microscope slide
Liquid Nitrogen	3 cycles of 4 hours at -196°C (-320°F)/8 hours at room temperature	◆ × ∨	Glass test tube Polypropylene centrifuge tube Glass microscope slide
Freezer to boiling water	1 hour at -70°C (-94°F) then placed in boiling water 100°C (212°F)	X X X	Glass test tube Polypropylene centrifuge tube Glass microscope slide
Liquid Nitrogen to boiling water	1 hour at -196°C (-320°F) then placed in boiling water 100°C (212°F) for 10 minutes	x x x	Glass test tube Polypropylene centrifuge tube Glass microscope slide

^{**} Samples for this testing were placed on glass panels and glass test tubes

✓ Label suitable for application; no visible effect, label remains adhered to test surface

Label may work in application; test results were mixed

Label not recommended for application; label came off either during testing or after test surface was removed from environment.

PERFORMANCE PROPERTIES CHEMICAL RESISTANCE

Samples of B-424 were printed with the Brady Series R4300 ribbon. Printed samples were laminated to glass microscope slides and allowed to dwell 24 hours prior to testing. Test conducted at room temperature. Samples were immersed in the test solvent for 15 minutes. The samples were removed and rubbed 10 times with a cotton swab saturated with the test fluid. The rating scale below shows the effect to the quality of the print for each sample.

CHEMICAL	SUBJECTIVE OBSERVATION OF VISUAL CHANGE		
REAGENT	EFFECTS TO LABEL	EFFECTS TO PRINTED IMAGE	
	STOCK	WITHOUT RUB	WITH RUB
Ethanol	No visible effect	1	1
Toluene	Label came off test	X	X
	surface		
Isopropanol	No visible effect	1	1
Chloroform	Label came off test	X	X
	surface		
Xylene	Label came off test	X	X
	surface		
Dimethylsulfoxide	No visible effect	1	5



CHEMICAL	SUBJECTIVE OBSERVATION OF VISUAL CHANGE			
REAGENT	EFFECTS TO LABEL	EFFECTS TO PRINTED IMAGE		
	STOCK	WITHOUT RUB	WITH RUB	
(DMSO)				
Methylene Chloride	Label came off test surface	X	X	
50% Acetic Acid	No visible effect	1	5	
10% Hydrochloric Acid	No visible effect	1	5	
10% Sodium Hydroxide	Label came off test surface	Х	X	
10% Chlorox Solution	Label came off test surface	Х	Х	

Rating Scale:

1=no visible effect

2=slight smear or print removal, detectable but minimal smear

3=moderate smear or print removal (print still legible)

4=severe smear or print removal (print illegible or just barely legible)

5=complete print and/or topcoat removal

NP=print removed prior to rub

Shelf Life:

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

References:

ASTM: American Society for Testing and Materials (U.S.A.)

All S.I. Units (metric) are mathematically derived from the U.S. Conventional Units

Note: All values shown are averages and should not be used for specification purposes.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2019 Brady Worldwide, Inc. | All Rights Reserved Material may not be reproduced or distributed in any form without written permission.