

B-8508 WHITE POLYESTER LABEL STOCK WITH PERMANENT, CLEANLY REMOVABLE ACRYLIC ADHESIVE MOUNTED ON A LOW EXTRACTABLE SILICONE POLYESTER RELEASE LINER

TDS No. B-8508
Effective Date: 06/27/2011

Description:

CONSTRUCTION

Substrate: 2 mil white polyester film
Adhesive Layer: 1 mil (BA165) removable acrylic pressure sensitive adhesive
Release Liner: 1.5 mil low extractable silicone polyester release liner

GENERAL

Print Technology: Thermal transfer
Material Type: White polyester
Finish: Glossy
Adhesive: Permanent, cleanly removable acrylic pressure sensitive

APPLICATIONS

B-8508 is designed as a chemically clean, cleanly removable, THT printable label for the Hard Disc Drive market. Other uses include rating plate applications that utilize high quality/density alphanumeric, barcodes and graphics.

RECOMMENDED RIBBONS

Brady Series R8961 black thermal transfer ribbons.

SPECIAL FEATURES

B-8508 is supplied with a permanent, yet cleanly removable, acrylic adhesive that exhibits stable adhesion over time to many surfaces.
B-8508 is also low out gassing, low ions, low tin and low silicone.

REGULATORY APPROVALS

Brady B-8508 is RoHS compliant to 2005/618/EC MCV amendment to RoHS Directive 2002/95/EC

Details:

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 -Substrate -Adhesive -Total	0.0020 inch (0.051 mm) 0.0010 inch (0.025 mm) 0.0030 inch (0.076 mm)
Adhesion to: (dwelled on panel for indicated time/temperature) -Stainless Steel -Aluminum -ECA (Epoxy-Coated Aluminum)	ASTM D 1000 20 minute dwell 24 hour dwell @ 70 °C 20 minute dwell 24 hour dwell @ 70 °C 20 minute dwell 24 hour dwell @ 70 °C	 39 oz/in (10.84N/25mm) 54 oz/in (15.01N/25mm) 33 oz/in (9.17N/25mm) 48 oz/in (13.34N/25mm) 34 oz/in (9.45 N/25mm) 68 oz/in (18.90 N/25mm)
Tack	ASTM D 2979 Polyken™ Probe Tack 1 second dwell	955 g
Shear Adhesion Failure Temperature (SAFT)	ASTM D 4498-95 (except use 25mm X 25mm X 1Kg)	> 200°C
Extractable Sn via ICP-MS	Seagate 35555-008	<25 ppb
Extractable ions	Seagate 20800012-001	Anions (µg/cm ²) Fluoride ND

		Chloride <0.005 Nitrite ND Bromide ND Nitrate <0.005 Phosphate ND Sulfate 0.005 Cations (µg/cm ²) Lithium ND Sodium <0.005 Ammonium <0.005 Potassium ND Magnesium ND Calcium ND ND = None Detected
DHS GC-MS outgassing	Seagate 20800020-001 Rev. E with constant flow	57 ng/cm ²

Product testing, customer feedback, and history of similar products, support a customer performance expectation of at least **one year from the date of receipt** for this product as long as this product is stored in its original packaging in an environmental below 80 degrees F and 60% RH. We are confident that our product will perform well beyond this time frame. However, it remains the responsibility of the user to assess the risk of using such product. We encourage customers to develop functional testing protocols that will quality a product's fitness for use, in their actual applications.

Trademarks:

ASTM: American Society for Testing and Materials (U.S.A.)
 PSTC: Pressure Sensitive Tape Council (U.S.A.)
 Polyken™ is a trademark of Testing Machines Inc.

Note: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship, but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use, Brady's products.

Copyright 2016 Brady Corporation Asia Pte. Ltd. | All Rights Reserved
 Material may not be reproduced or distributed in any form without written permission.