



GENERAL PRODUCT SPECIFICATION

Item No.	CH30DP
-----------------	--------

Date	16-6-2017	Replaces	12-09-13	No. Pages	1
-------------	-----------	-----------------	----------	------------------	---

Product Description:

Style	Blanket Roll; high strength perforation down the middle for the 15” wide dimension, & cross-wise for the 15” long dimension.
Item Size (each)	76cm x 46m (240 pads per roll)
Color	Yellow
Composition	100% Polypropylene
Structure	A 3-ply non-woven mat of randomly oriented meltblown micro-fibers [2-10 micron diameters] One side having a Yellow lint & abrasion resistant spunbond cover-stock (non-woven, continuous filaments randomly oriented and thermally point bonded [15-30 micron diameters]). Other side is meltblown Coverstock The (3) plies are secured together with bonded dimpling.
Technology	Spunbond , Meltblown & Meltblown Coverstock
Absorbency	Universal (Hydrophilic + Oleophilic)
Bonding	Bonded (staggered pattern) + Mechanical entanglement

Intended Application	Abrasion Resistant, Lint Resistant, & Chemical Resistant Sorbent for Oil or Solvent Base Liquids
-----------------------------	--

Absorbency Capacity	147l per bale (saturated; medium viscosity-12.5x)
----------------------------	---

Packaging Description:

Package configuration	Case	Pkg. Weight	11.4kg (10,1kg)
Items per Package	1 Bale / Case	Pkg. Dimensions	45 cm x 45 cm x 80 cm (H)
Container type	Carton		

Physical Properties;

Parameter	SPC Test Method	Units	Nominal	(+/-)Tolerance
Basis Weight	SPCTM-002A	G/M2	290	29
Caliper	SPCTM-003A	mils	175	17
Absorbency ** (med. Oil)	SPCTM-004B	gL/gS	12.5	2
Tensile Strength	SPCTM-007	lbs	18	2
Color	Visual	-----	Yellow	per standard

The above properties are “nominal” values used for **PROCESS CONTROL** when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.