

## **TECHNICAL DATA SHEET**

Order reference	DTA-25
Article number	813795

Date	03-16-06		Replaces	2-24-06		No. Pages	1
------	----------	--	----------	---------	--	-----------	---

## **Product Description:**

Style	Drum Top Cover
Item Size (each)	56 cm diameter
Color	Gray
Composition	Polypropylene >98%, Surfactant < 1.0%, color pigment < 0.1 %
Structure	A nonwoven mat of randomly oriented Micro-fibers [2-10 micron diameters]
Technology	Meltblown, 3-ply
Absorbency	Universal ( <b>Hydrophilic</b> + Oleophilic)
Bonding	Ultrasonic "Oil Drop Dimple" staggered pattern + Mechanical entanglement

<b>Intended Application</b>	Drum Top Cover of Low -Lint Chemical Resistant Sorbent for Water, Oil, or
	Solvent Base Liquids

<b>Absorbency Capacity</b> 26 l per bale (saturated; medium viscosity-12.5x)	
--	--

## **Packaging Description:**

Package configuration	Case	Pkg. Weight	2.6 kg (1.8kg)
Items per Package	25-Pads/Case	Pkg. Dimensions	57cm x 57cm x
			9cm H
Container type	Carton		

## **Physical Properties**;

111,510411105010105				
<u>Parameter</u>	SPC Test Method	Units	Nominal	(+/-)Tolerance
Basis Weight	SPCTM-002A	G/M2	290	30
Caliper	SPCTM-003A	mm	4.5	0.4
Absorbency** (med.	SPCTM-004B	gL/gS	12.5	2
Oil)				
Tensile Strength	SPCTM-007	daN	7.3	0.7
Color	Visual		Gray	per standard

The above properties are "nominal" values used for PROCESS CONTROL when the product is produced and/or inspected. Performance "nominals" may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.
\*\* The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No.,
	Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer.
	Claims for non-conformance of goods must be made within 60-days of delivery.