

## **GENERAL PRODUCT SPECIFICATION**

Item No. GP150-P-E

Date	16-6-2017	Replaces	24-09-14	No. Pages	1

Blanket roll, high strength perforation every 44 cm for single or
multiple/variable length pads
96 cm wide by 44 m long (100 Pads)
Gray
Polypropylene >98%, Surfactant < 1.0%, color pigment < 1.0 %
A nonwoven mat of randomly oriented Micro-fibers [2-10 micron diameters]
Meltblown
Universal (Hydrophilic + Oleophilic)
Bonded (staggered pattern) + Mechanical entanglement
-

Intended Application Chemical Resistant Sorbent for Water, Oil, or Solvent Base Liquids

Absorbency Capacity192 l per box (saturated; medium viscosity-14x)

## **Packaging Description:**

Package configuration	Bale	Pkg. Weight	12.0 kg (11.8kg)
Items per Package	1 Blanket Roll/Bale	Pkg. Dimensions	43cm x 43cm x 98cm (H)
Container type	Polybag + Twist tie		

## Physical Properties;

Parameter	SPC Test Method	<u>Units</u>	<u>Nominal</u>	(+/-)Tolerance
Basis Weight	SPCTM-002A	G/M2	280	28
Caliper	SPCTM-020	mm	4.6	0.4
Absorbency ** (med.	SPCTM-004B	gL/gS	14	2
Oil)				
Tensile strength	SPCTM-007	daN	6.3	0.6
Color	Visual		Gray	per standard

The above properties are "nominal" values used for PROCESS CONTROL when the product is produced and/or inspected. Performance "nominals" may vary depending upon the specific application, and/or the environment being applied, stored, or shipped. \*\* The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No.,
_	Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer.
	Claims for non-conformance of goods must be made within 60-days of delivery.