

GENERAL PRODUCT SPECIFICATION

Item No.	MS50				
Date	16-6-2017	Replaces	10-03-08	No. Pages	1

Product Description:

Style	SOC	
Item Size (each)	76 mm x 1.2 m	
Color	Gray with red logo printing	
Composition	> 99% Cellulose, < 1% Spundbond	
Structure	Sorbent fill: Micro-fibrous Cellulose	
	Outer covering: Spunbond polypropylene nonwoven (15-30 micron dia. fiber)	
Technology	Cellulose + Spunbond + Sealed or Enclosed Ends	
Absorbency	Hydrophilic + Oleophilic	

Intended Application	"Universal" Sorbent Sock for Non-Aggressive Spills of Water Base, Oil Base,
	or Solvent Base Liquids

Absorbonari Congaitri	151 Learn aggs (activated, medium vigagaity, 9.5v)
Absorbency Capacity	151 l per case (saturated; medium viscosity- 8,5x)

Packaging Description:

Package configuration	Case	Pkg. Weight	16.3 kg (15.3kg)
Items per Package	40 Socs/Case	Pkg. Dimensions (approx.)	60 cm x 40 cm x 76 cm (H)
Container type	Carton		

Physical Properties;

<u>Parameter</u>	SPC Test Method	<u>Units</u>	<u>Nominal</u>	(+/-)Tolerance
SOC Weight	Gravimetric	kg	0.45	0.045
Absorbency** (med.	SPCTM-012B	gL/gS	8.5	6-min.
oil)				
Color	Visual		Gray	per standard

The above properties are "nominal" values used for PROCESS CONTROL when the product is produced and/or inspected. Performance "nominals" may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

** The "Absorbency" Spec and "SPCTM012" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.		
Labeling	Each package to be clearly labeled with Company Name, Address, Item No.,		
	Date, and/or Package Code (Bar Code).		
Certification	ification Make no changes in basic process or composition without notifying custome		
	Claims for non-conformance of goods must be made within 60-days of delivery.		