

TECHNICAL DATA SHEET

| Order reference | OIL124 |
|-----------------|--------|
| Article number | 813778 |

| Date 4-11-11 Replaces 6-29-06 No. Pages 1 | 4-11-11 Replaces 6-29-06 No. Pa | ges 1 |
|--|---|-------|
|--|---|-------|

Product Description:

| | - | |
|------------------|---|--|
| Style | SOC | |
| Item Size (each) | 7.6 cm d x 366 cm long | |
| Color | White with blue logo printing | |
| Composition | 100% Polypropylene | |
| Structure | Sorbent fill: Micro-fibrous meltblown polypropylene (2-10 micron diameters) | |
| | Outer covering: Spunbond polypropylene nonwoven (15-30 micron dia. fiber) | |
| Technology | Meltblown + Spunbond + Sealed or Enclosed Ends | |
| Absorbency | Hydrophobic + Oleophilic | |

| Intended Application | Chemical Resistant Sorbent Sock for Spills of Oil Base or Solvent Base | | | |
|----------------------|--|--|--|--|
| | Liquids | | | |

| Absorbency Capacity | 43 1 per case (saturated; medium viscosity- 9x) |
|---------------------|---|

Packaging Description:

| Package configuration | Case | Pkg. Weight | 5.0 kg (4.1 kg) |
|-----------------------|-------------|---------------------------|-------------------------|
| Items per Package | 4 SOCS/Case | Pkg. Dimensions (approx.) | 56.5 cm x 32cm x 37.5cm |
| Container type | Carton | | |

Physical Properties;

| <u>Parameter</u> | SPC Test Method | <u>Units</u> | Nominal Nominal | (+/-)Tolerance |
|-------------------------|-----------------|--------------|-----------------|----------------|
| SOC Weight | Gravimetric | kg | 1.02 | 0.27 |
| Absorbency** (med. oil) | SPCTM-012B | gL/gS | 9 | 8-min. |
| Color | Visual | | White | per standard |

The above properties are "nominal" values used for PROCESS CONTROL when the product is produced and/or inspected. Performance "nominals" may vary depending upon the specific application, and/or the environment being applied, stored, or shipped. ** The "Absorbency" Spec and "SPCTM012" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

| Attributes | Product will be free of foreign material contamination, rips, holes, and tears. | | |
|---------------|---|--|--|
| Labeling | Each package to be clearly labeled with Company Name, Address, Item No., | | |
| | Date, and/or Package Code (Bar Code). | | |
| Certification | Make no changes in basic process or composition without notifying customer. | | |
| | Claims for non-conformance of goods must be made within 60-days of delivery. | | |