



TECHNICAL DATA SHEET

Order reference	OP30-DP-E				
Article number	813756				
Date	4-11-11	Replaces	03-31-08	No. Pages	1

Product Description:

Style	Blanket Roll; high strength perforation down the middle for the 38 cm wide dimension, & cross-wise for the 38 cm long dimension.
Item Size (each)	76 cm wide by 46 m long (240 pads per roll)
Color	White
Composition	100% Polypropylene
Structure	96% natural white meltblown nonwoven fibers(<10 microns) 4% white spunbond nonwoven coverstock(<15-30 microns)
Technology	Meltblown + spunbond
Absorbency	Hydrophobic + Oleophilic
Bonding	Bonded (staggered pattern) + Mechanical entanglement

Intended Application	Low -Lint Chemical Resistant Sorbent for Oil or Solvent Base Liquids for single or multiple/variable length pads.
-----------------------------	---

Absorbency Capacity	187 l per Roll (saturated; medium viscosity-12.5x)
----------------------------	--

Packaging Description:

Package configuration	1 Case	Pkg. Weight	14.6 kg (12.9 kg)
Items per Package	1 Roll / Case (240 pads)	Pkg. Dimensions	45.5cm x 45.5cm x 79cm H
Container type	Carton		

Physical Properties:

<u>Parameter</u>	<u>SPC Test Method</u>	<u>Units</u>	<u>Nominal</u>	<u>(+/-)Tolerance</u>
Basis Weight	SPCTM-002A	g/m ²	365	36
Caliper	SPCTM-020	mm	5.4	0.5
Absorbency ** (med. Oil)	SPCTM-004B	gL/gS	12.5	2
Tensile Strength	SPCTM-007	daN	13.8	1.3
Color	Visual	-----	White	per standard

The above properties are “nominal” values used for PROCESS CONTROL when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

**** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.