

GENERAL PRODUCT SPECIFICATION

Item No. OP365-P

| Date 16-6-2017 Replaces 18-4-2014 | | No. Pages | 1 |
|-----------------------------------|--|-----------|---|
|-----------------------------------|--|-----------|---|

Product Description:

| <u>I I Oudet Deseriptioni</u> | | |
|-------------------------------|--|--|
| Style | Blanket Roll; high strength perforation every 25 cm for single or | |
| | multiple/variable length pads | |
| Item Size (each) | 19 cm wide by 15 m long (60 pads per roll) | |
| Color | White | |
| Composition | 100% Polypropylene | |
| Structure | 96% natural white meltblown nonwoven fibers(<10 microns) | |
| | 4% white spunbond nonwoven coverstock (15 microns) | |
| Technology | Meltblown + spunbond | |
| Absorbency | Hydrophobic + Oleophilic | |
| Bonding | Bonded (staggered pattern) + Mechanical entanglement | |
| | | |
| Intended Application | Low -Lint Chemical Resistant Sorbent for Oil or Solvent Base Liquids | |

Absorbency Capacity 15 1 per Roll (saturated; medium viscosity-12.5x)

Packaging Description:

| Package configuration | Case | Pkg. Weight | 1.1 kg (1.0 kg) |
|-----------------------|--------------|-----------------|-----------------|
| Items per Package | 1 Roll / Bag | Pkg. Dimensions | 25 cm x 25 cm x |
| | | | 20 cm (H) |
| Container type | Carton | | |

Physical Properties;

| <u>Parameter</u> | SPC Test Method | <u>Units</u> | <u>Nominal</u> | (+/-)Tolerance |
|--------------------|-----------------|--------------|----------------|----------------|
| Basis Weight | SPCTM-002A | g/m2 | 365 | 36 |
| Caliper | SPCTM-020 | mm | 5.2 | 0.5 |
| Absorbency** (med. | SPCTM-004B | gL/gS | 12.5 | 2 |
| Oil) | | | | |
| Tensile Strength | SPCTM-007 | daN | 20 | 2 |
| Color | Visual | | White | per standard |

The above properties are "nominal" values used for PROCESS CONTROL when the product is produced and/or inspected. Performance "nominals" may vary depending upon the specific application, and/or the environment being applied, stored, or shipped. ** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

| Attributes | Product will be free of foreign material contamination, rips, holes, and tears. |
|--|---|
| Labeling | Each package to be clearly labeled with Company Name, Address, Item No., |
| _ | Date, and/or Package Code (Bar Code). |
| Certification | Make no changes in basic process or composition without notifying customer. |
| | Claims for non-conformance of goods must be made within 60-days of delivery. |
| SPC International Atealaan 71 LZ Klein Gent B-2200 Herentals Belgium | |

C International, Atealaan 71, I.Z. Klein Gent, B-2200 Herentals,Belgium Tel +32(0)14 321855 Fax +32(0)14 320440 www.bradyeurope.com